

AMENDMENTS TO THE CLAIMS

The following is a complete, marked up listing of revised claims with a status identifier in parentheses, underlined text indicating insertions, and strikethrough and/or double-bracketed text indicating deletions.

LISTING OF CLAIMS

1. (Currently Amended) A method for ~~treating a polymeric optical element, post-processing~~
of an amorphous, transparent polymeric optical element, which comprises:
 - a) mounting ~~an~~ an amorphous polymeric optical element into a chamber;
 - b) introducing a compressed gas in a supercritical phase or a liquid or vapor phase
approaching the supercritical phase as an annealing medium into the chamber and
annealing the amorphous polymeric optical element; and
 - c) removing the annealing medium from the chamber.
2. (Currently Amended) The method of claim 1, wherein the amorphous polymeric optical element is made of an amorphous transparent polymer.
3. (Currently Amended) The method of claim 2, wherein the amorphous polymeric optical element is selected from the group consisting of polycarbonate, polystyrene, poly(methacrylate), poly(methyl-methacrylate), poly(trifluoro-methyl-methacrylate), poly(tetra-propyl-fluoro-methyl-methacrylate), Teflon AF, and cytop.
4. (Currently Amended) The method of claim 1, wherein the amorphous polymeric optical element is a plastic optical fiber.
5. (Previously Presented) The method of claim 1, wherein the annealing medium is a compressed gas in a liquid or vapor phase approaching supercritical phase.
6. (Previously Presented) The method of claim 1, wherein the compressed gas is a solvent or a non-solvent material for the polymeric optical element, or a mixture thereof.

7. (Original) The method of claim 6, wherein the annealing medium is a material selected from the group consisting of CO₂, SF₆, C₂H₆, CCl₃F, CClF₃, CHF₃, and isopropanol.
8. (Original) The method of claim 1, wherein, in step b), the annealing is performed with a variation of temperature and pressure conditions of the annealing medium.
9. (Original) The method of claim 1, wherein, in step b), temperature and pressure of the annealing medium are varied according to a periodic or non-periodic function.
10. (Currently Amended) An amorphous polymeric optical element produced by the method of claim 1.
11. (Currently Amended) A method for ~~treating a polymeric optical element, post-processing of an amorphous transparent polymeric optical element,~~ which comprises:
annealing the amorphous polymeric optical element in a compressed gas, wherein the compressed gas is in a supercritical phase or a liquid or vapor phase approaching the supercritical phase, an annealing medium, and recovering the annealed amorphous polymeric optical element.
12. (Original) The method of claim 11, wherein the annealing is conducted at a temperature of about 10 to 100° C and a pressure of 2 to 200 atm.
13. (Currently Amended) The amorphous polymeric optical element of claim 10 which is a plastic optical fiber having a core and a clad, said core being made of polymethyl methacrylate and said clad being made of a copolymer of methyl methacrylate and tetrafluoropropyl methacrylate.